



TECHNICAL SPECIFICATIONS

		Test
Recommended Install Temp Range	40 degrees F - 100 degrees F	
Impact Resistance	134.5 lbs	ASTM D 3679
Average Gloss	22.3	ASTM D 2457
Surface Distortion	No Distortion @ 180degF	ASTM D 3679
Coefficient of Linear Thermal Expansion	6.24x10(-5) mm/mm degC	ASTM D 696
Color Uniformity	delta E =0.47	ASTM D 2244
Dynamic Wind Loading	No Damage @ 90 mph for 5 min	ASTM E 330-02
Max Joist Bracket Spacing	20"	
Max Joist Spacing	16"	
Max Section Span	16' 2.5"	

• Barbeque grills, portable propane heaters, fire pits and outdoor fireplaces should not be used under the living space protected by DrySnap®. Heat generated from these devices can damage the DrySnap®.

• For decks with Joist Spacing greater than 16" o.c., it is recommended that you first install 1"x4" pressure treated furring strips below & across the joists where rows of joist brackets are to be positioned.